

K-Bond MEA

Multi-Purpose Epoxy Adhesive.

DESCRIPTION

K-Bond SBR MEA is a multi-component epoxy resin-based adhesive specially formulated from graded fillers and non-sagging agents which makes it ideal for application on vertical surfaces. Designed for application for use in vertical, horizontal and overhead surfaces.

USES

Bonds most used construction materials, such as

- Rubber
- Concrete
- Wood
- Metals
- Natural stones, etc.

ADVANTAGES

- High strength
- Resistant to wide range of chemicals
- Non-toxic
- Can be used in contact with potable water
- Can be over coated

PHYSICAL PROPERTIES*

PROPERTY	TYPICAL RESULTS
Volume solids	100
Density	1.5
Compressive strength	>65 MPa – at 28 days
Flexural Strength	>20 MPa – at 28 days
Tensile strength	>12 MPa – at 28 days
Appearance	Grey

*The above properties are average laboratory values

PACKAGING

K-Bind MEA is available in 3 kg kit.

THEORETICAL COVERAGE RATE.

1.5 kg/m² at 1mm thickness.

Actual coverage rates will depend on wastage and substrate profile.

SHELF LIFE

12 months when stored in factory packed unopened pack, stored in a cool dry and elevated place away from direct sunlight.

APPLICATION PROPERTIESSES

PROPERTY	TYPICAL RESULTS
Application temperature	5°C to 40°C
Minimum thickness	1mm
Minimum thickness	5mm
Initial cure	6 hours @25°C
Full cure	7 days

INSTALLATION GUIDELINES

Kenal provides detailed method statements on all its products for use in various applications. These must be referred to prior to starting the work. The information below is a summary intended for guidance only.

Surface Preparation

Substrate must be structurally sound. Loose or unsound materials should be removed. Surfaces must be entirely free of oil, grease, paint, corrosion deposits, dust, laitance or other surface deposits. The substrate must be prepared to create a 'key' for bonding.

PRIMING

The substrateK must be clean, primer not necessary prior to application.

MIXING

Thoroughly mix the base 'Part A' prior to adding the hardener 'Part B' using a slow speed drill (500rpm) fitted with a mixing paddle. After mixing the base, add all of the hardener to the base and mix for 1-2 minute until both components have fully dispersed and are uniform in color. Be sure to rotate the mixer throughout the drum.

Mix full packs, part mixing not recommended.

APPLICATION

Application can be carried out by a steel trowel or putty knife or scraper. Press firmly the mixed mortar into the area to be filled to ensure proper adhesion and full

TECHNICAL DATA SHEET



contact. The epoxy adhesive shall be applied at a maximum thickness of 5mm in one layer. Additional layers should be applied after the applied mortar achieves its initial cure.

CLEANING

Clean all the tools with **K-Clean** solvent immediately after use. Hardened materials can be removed mechanically only.

PRECAUTIONS

- Do not add additional solvent or re-temper the mix. Ensure the temperature of the filler does not exceed
- 35°C at the time of mixing. Do not part mix, use full kit.
- Do not apply in rain or wet conditions or at temperature below 5°C.
- Do not expose to running water until the product is fully cured for 7 days.

TECHNICAL SUPPORT

Kenal-offers full technical support package to specifiers, contractors and end users as well as technical assistance on site and after sales consultations.

HEALTH & SAFETY

As with all chemical products, caution should always be exercised. Protective clothing, such as gloves and goggles, should be worn. See packaging/MSDS for specific instructions.

Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.